



Technical information sheet

DESCRIPTION

Shuangshi No-reinforced TPO is a flexible Thermoplastic Polyolefin membrane that is produced with polypropylene and ethylene-polypropylene, TPO(thermoplastic polyolefin) is a single-ply membrane used widely in low-slope or flat roofing systems. Our shuangshi No-reinforced TPO membrane meets or exceeds all requirements for ASTM D 6878 Specification. The colour and thickness can be customized according to requirement, in general, the typical color is white, typical thickness is 45 mil (1.14 mm) and 60 mil (1.52 mm) .

METHOD OF APPLICATION

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose, or foreign materials, oil, grease, and other materials that may damage the membrane.
2. All rough surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than 1/4" (6.3 mm) wide shall be properly filled with an acceptable fill material.
4. Shuangshi TPO membrane is installed as continuous roofing or waterproofing layer on the roof. Rolls are overlapped (side laps and end laps) prior to heat welding the seam areas.

STORAGE

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.

PRECAUTIONS

- Exercise caution when lifting, moving, transporting, storing, or handling membrane rolls to avoid sources of punctures and possible physical damage.
- Refer to Safety Data Sheets (SDS) for additional safety information.



| Typical Properties | | | | |
|--|---------------------------------|-------------------------------------|-----------------------------------|-----------------------------------|
| Properties | ASTM Standard | Performance Minimum | Typical Performance 45 mil | Typical Performance 60 mil |
| Overall Thickness | D 751 | 0.039" (1 mm) | 0.045" (1.14 mm) ± 10% | 0.060" (1.52 mm) ± 10% |
| Breaking Strength | D 751, Grab Method | 220 lbf (979 N) | 270lbf (1,200 N) | 300 lbf (1,335 N) |
| Elongation of Reinforcement Break | D 751, Grab Method | 15% | 30% | 30% |
| Tearing Strength | D 751 | 55 lbf (245 N) | 100lbf (445N) | 100 lbf (445N) |
| Brittleness Point | D 2137 | -40 ° F (-40 ° C) | Pass | Pass |
| Puncture Resistance | FTM 101C, Method 2031 | --- | 260 (1,150) | 275 (1,224) |
| Ozone Resistance, No Cracks | D 1149 | Pass (No Cracks) | Pass | Pass |
| Properties After Heat Aging (Retained Values) ASTM D 573-5376 h (224 days or 32 weeks) at 240 °F (116 °C) | | | | |
| Breaking Strength | D 751, Grab Method | 90% Minimum | > 90% | > 90% |
| Elongation at Break | D 751, Grab Method | 90% Minimum | > 90% | > 90% |
| Tearing Strength | D 751 | 60% Minimum | > 60% | > 60% |
| Weight of Change | --- | ± 1% Maximum | < 1% | < 1% |
| Linear Dimension Change | D 1204, 6 h at 158 ° F (70 ° C) | ± 1% Maximum | < 1% | < 1% |
| Water Absorption | D 471 | ± 3% Maximum | < 3% | < 3% |
| Weather Resistance* | G 155 | 10,800 kJ/m ² Minimum | Pass | Pass |



TPO optional specifications and sizes.

| Membrane Thickness: 0.045" (1.14 mm) | | Membrane Thickness: 0.060" (1.52 mm) | |
|---|------------------|---|------------------|
| Membrane Weight: 0.23 lb/ft ² (1.1 kg/m ²) | | Membrane Weight: 0.31 lb/ft ² (1.5 kg/m ²) | |
| Available Sizes | Available Colors | Available Sizes | Available Colors |
| 5' x 100' (1.5 x 30.5 m) | White, Tan, Gray | 5' x 100' (1.5 x 30.5 m) | White, Tan, Gray |
| 5' x 200' (1.5 x 61 m) | White | 5' x 200' (1.5 x 61 m) | White |
| 6' 2" x 100' (1.9 x 30.5 m) | White, Tan, Gray | 6' 2" x 100' (1.9 x 30.5 m) | White, Tan, Gray |
| 8' x 100' (2.4 x 30.5 m) | White, Tan, Gray | 8' x 100' 2.4 x 30.5 m) | White, Tan, Gray |
| 8' x 200' (2.4 x 61 m) | White | 8' x 200' (2.4 x 61 m) | White |
| 10' x 100' (3.0 x 30.5 m) | White, Tan, Gray | 10' x 100' (3.0 x 30.5 m) | White, Tan, Gray |
| 10' x 200' (3.0 x 61 m) | White | 10' x 200' (3.0 x 61 m) | White |
| 12' 4" x 100' (3.8 x 30.5 m) | White, Tan, Gray | 12' 4" x 100' (3.8 x 30.5 m) | White, Tan, Gray |
| 12' 4" x 200' (3.8 x 61 m) | White | 12' 4" x 200' (3.8 x 61 m) | White |